

Dhara

Colorker®

Colores
Colours



Sand

Taupe

White

Ash

V2 Variación cromática leve
Slight Colour Variation

G3 Variación gráfica media
Moderate Graphic Variation

P Porcelánico
Porcelain



























Pavimento
Floor tiles

Revestimiento
Wall tiles

Resistencia la helada
Frost resistance

Medida nominal (cm) Nominal size	Espesor - E (mm) Thickness - E	Tipología Topology	Deslizamiento Coefficient of friction
31,6x100 ^R	9,7	BIII-GL	-
31,6x100 ^R Decor	10,4	BIII-GL	-
29,5x59,5 ^R Gloss	9,1	BIII-GL	-
29,5x59,5 ^R Lines	10,4	BIII-GL	-
120x120 ^R	9,0	Bla-UGL	CLASE-1
120x120 ^R Grip + (Sand / White)	9,0	Bla-UGL	CLASE-3 / R11C
60x120 ^R Duplo	20	Bla-UGL	CLASE-3 / R11 C
59,5x119,2 ^R	8	Bla-UGL	CLASE-1
59,5x119,2 ^R Decor	10,3	Bla-UGL	CLASE-1
59,5x59,5 ^R	8	Bla-UGL	CLASE-1
59,5x119,2 ^R Grip +	8	Bla-UGL	CLASE-3 / R11 C
29,5x59,5 ^R	8	Bla-UGL	CLASE-1
29,5x59,5 ^R Decor	8,8	Bla-UGL	CLASE-1
14,5x59,5 ^R	8	Bla-UGL	CLASE-1

CARACTERÍSTICAS TÉCNICAS TECHNICAL FEATURES

	ISO 13006 UNE-EN 14411	Bla    	BIIb  	BIII 
 Longitud y anchura Length and width	EN ISO 10545-2	± 0,6 % ± 2,0 mm	± 0,6 % ± 2,0 mm	± 0,5 % ± 2,0 mm
 Espesor Thickness	EN ISO 10545-2	± 5 % ± 0,5 mm	± 5 % ± 0,5 mm	± 10 % ± 0,5 mm
 Rectitud de lados Straightness of sides	EN ISO 10545-2	± 0,5 % ± 1,5 mm	± 0,5 % ± 1,5 mm	± 0,5 %
 Ortogonalidad Rectangularity	EN ISO 10545-2	± 0,5 % ± 2,0 mm	± 0,5 % ± 2,0 mm	± 0,3 % ± 1,5 mm
 Planitud de superficie Surface flatness	EN ISO 10545-2	± 0,5 % ± 2,0 mm	± 0,5 % ± 2,0 mm	+ 0,5 % ; - 0,3 % + 2 mm ; - 1,5 mm
 Absorción de agua Water absorption	EN ISO 10545-3	E ≤ 0,5 % Max. Individual 0,6%	0,5 % ≤ E ≤ 3 %	E > 10 %
 Fuerza de rotura (N)* Breaking strength*	EN ISO 10545-4	E > 7,5 mm > 1300 NE < 7,5 mm > 700 N	E > 7,5 mm > 1100 NE < 7,5 mm > 700 N	E > 7,5 mm > 600 NE < 7,5 mm > 200 N
 Resistencia a la flexión (N/mm ²) Modulus of rupture	EN ISO 10545-4	> 35 N/mm ² Min. Individual 35 N/mm ²	> 35 N/mm ² Min. Individual 27 N/mm ²	E > 7,5 > 12 N/mm ² E < 7,5 > 15 N/mm ²
 Resistencia a la abrasión profunda (Solo UGL) Surface deep abrasion resistance (Only UGL)	EN ISO 10545-6	Máx. 175 mm ³	Máx. 175 mm ³	No aplica Not apply
 Resistencia a la abrasión superficial (Solo GL) Surface abrasion resistance (Only GL)	EN ISO 10545-7	Valor declarado Declared value	Valor declarado Declared value	No aplica Not apply
 Coeficiente de dilatación térmica lineal (1/k) Coefficient of linear thermal expansion	EN ISO 10545-8	Valor declarado Declared value	Valor declarado Declared value	Valor declarado Declared value
 Resistencia al choque térmico Thermal shock resistance	EN ISO 10545-9	Resiste Resist	Resiste Resist	Resiste Resist
 Resistencia al cuarteo Crazing resistance	EN ISO 10545-11	Resiste Resist	Resiste Resist	Resiste Resist
 Resistencia a la helada Frost resistance	EN ISO 10545-12	Resiste Resist	No resiste Not resist	No resiste Not resist
 Deslizamiento Coefficient of friction	UNE ENV 41901 DIN 51130 DIN 51097 ANSI A137.1	Valor declarado Declared value	Valor declarado Declared value	No aplica Not apply
 Resistencia a productos de limpieza y aditivos para piscina Resistance to household chemicals and swimming pool salts	EN ISO 10545-4	Min GB	Min GB	Min GB
 Resistencia a bajas concentraciones Resistance to low concentrations	EN ISO 10545-13	GLA -ULA/ GLB (Pulido, Ecco, Nawan)	GLA	GLA
 Resistencia a altas concentraciones Resistance to high concentrations	EN ISO 10545-13	GHA-UHA /GHB (Pulido, Ecco, Nawan)	GHA	GHA
 Resistencia a las manchas Resistance to stains	EN ISO 10545-14	> 3	> 3	> 3

Las características indicadas son generales por grupo de absorción, para características concretas de modelo y color solicitar la ficha técnica correspondiente. The characteristics indicated are general for each absorption group, for specific characteristics of the model and color, please request the corresponding technical data sheet.

* E corresponde al espesor indicado en la tabla de la esquina superior derecha. E is the thickness shown in the upper right-hand corner of table.